

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.



Ottawa Hull K1A 0C9

(21) (A1) 2,105,887  
(22) 1993/09/10  
(43) 1994/03/11

(51) INTL.CL.<sup>5</sup> A61K-009/00

(19) (CA) **APPLICATION FOR CANADIAN PATENT** (12)

(54) Bioerodible Device for Administering Active Ingredients

(72) Britton, Peter - U.S.A. ;  
Flanagan, Patricia - U.S.A. ;  
Hart, William P. - U.S.A. ;  
Linkin, Deborah - U.S.A. ;

(71) Same as inventor

(30) (US) 07/943,360 1992/09/10  
(US) 08/104,785 1993/08/16

(57) 42 Claims

5,072,7/55

Notice: This application is as filed and may therefore contain an incomplete specification.



Industrie Canada Industry Canada

3488

Canada

2105887

BIOERODIBLE DEVICE FOR ADMINISTERING ACTIVE INGREDIENTS

Abstract of the Disclosure

5 The invention relates to a muco-adherent, soluble  
device for administering active ingredients, a method of  
using said device, and an improved method of  
manufacturing said device using a continuous, enclosed  
mixing device capable of operating under pressure. The  
10 devices of the invention, which comprise a lyophilized  
foam and an active ingredient, have a dissolution time  
of at least about 8 hours, and preferably at least about  
24 hours, and can provide for the sustained and/or  
controlled release of an active ingredient for up to  
about 24 hours.

15

CHIC-802

BIOERODIBLE DEVICE FOR ADMINISTERING ACTIVE INGREDIENTS

5

Background of the Invention

10 The invention relates to a bioerodible device for administering active ingredients, said device being intended to be inserted into a body cavity. More particularly, it relates to a bioerodible device comprising a water-soluble muco-adherent lyophilized foam and an active ingredient; a method of using such devices; and a method for manufacturing such devices. The delivery  
15 device of the present invention adheres to mucosal tissue and is accordingly particularly suitable for use in administering active ingredients to both the buccal cavity and the vaginal cavity. The delivery device is used to provide for the controlled and sustained release of an  
20 active ingredient.

Prescription and over-the-counter medications and other pharmaceutical products have traditionally been administered through oral ingestion, nasal sprays,  
25 injection and suppositories. There are disadvantages associated with each of these methods of administration.

For example, with respect to oral ingestion of a drug, many patients, including pediatric and geriatric patients,  
30 frequently have great difficulty swallowing a pill. In addition, there is often a substantial delay between the time of oral administration of a drug until it has the desired therapeutic effect in the patient's system. Generally, a drug must pass from the stomach into the

small and large intestines before it will be absorbed  
int the patient's bloodstream. This typically takes  
about forty-five minutes or longer. Moreover, many drugs  
that are taken orally are metabolized almost immediately  
5 and thereby rendered ineffective by the patient's system  
before they can have the desired therapeutic effect.

Likewise, many patients also have at least some aversion  
to injections or suppositories. Moreover, neither of  
10 these methods are readily conducive to self-  
administration.

Consequently, many patients simply fail to comply with  
their physicians orders with respect to taking medications  
15 that are administered in these ways.

Compressed tablets or extruded thin films, including  
multi-layered products, that are inserted into the buccal  
cavity for delivering an active ingredient are known in  
20 the art. See, for example, U.S. Patent No. 4,540,566,  
Davis et al. which discloses a compressed tablet  
comprising cellulose ether; U.S. Patent No. 4,389,393,  
Schor et al., which describes a buccal delivery system  
consisting of a compressed tablet comprised of  
25 hydroxypropylmethylcellulose, or a mixture of  
methylcellulose and sodium carboxymethylcellulose, and/or  
other cellulose ethers; U.S. Patent Re. No. 33,093, issued  
to Schiraldi et al.; U.S. Patent No. 4,900,552, which  
discloses a trilaminate film comprised of a hydratable  
30 muco-adhesive base layer, a non-adhesive reservoir layer  
and a water-impermeable carrier film; U.S. Patent No.  
4,900,554, issued to Yanagibashi et al., wherein there is  
disclosed an adhesive device containing an adhesive layer  
and a water insoluble or sparingly soluble backing layer;

and G.B. Patent No. 2,108,841, which also discloses a multi-layered product comprising a non-adhesive layer and an adhesive layer.

- 5        However, although these devices are useful, there are also disadvantages associated with their use which renders them unsuitable for many applications and unacceptable to the patient. For example, many of these devices do not last very long. In U.S. Patent Nos. 4,717,723 and 4,829,056,  
10        Sugden discloses a compressed tablet for dispensing prochlorperazine or etorphine (or a salt thereof), respectively. Sugden's devices are intended to remain in position and dispense a drug for up to 2 hours. Likewise, in European Patent Application No. 371,466, there is  
15        described a buccal tablet for administering estradiol that is designed to dissolve very rapidly (that is, in about one minute). Accordingly, these devices are not suitable when clinical indications require a longer release time.
- 20        Furthermore, the hardness of the devices makes them highly uncomfortable when placed in the buccal cavity. In addition, they are inconvenient to apply, bulky, and difficult to keep in place.
- 25        In the area of foams, although the use of foams and freeze-dried foams to deliver various active ingredients is well-known, such foams generally do not possess the requisite characteristics that would render them suitable for use as a muco-adherent delivery device. For example,  
30        in U.S. Patent No. 4,642,903, Davies discloses the use of freeze-dried foams for dispensing a variety of active ingredients. However, Davies' foams are designed to have very rapid dissolution times (virtually instantaneous) which would render those foams highly ineffective for use

as an active ingredient dispensing device when longer release times are required. Moreover, in Davies' foaming process it is not possible to control the degree of aeration which is critical in order to manufacture batches of devices having substantially equivalent properties. Accordingly, using Davies' method it is not possible to control the density, dosages, dosage delivery rate and dissolution time of the devices from manufactured batch to manufactured batch.

Similarly, in U.S. Patent No. 4,292,972, Pawelchak et al. discloses a lyophilized foam sponge product containing sodium carboxymethylcellulose, pectin, gelatin, and a pharmaceutical, that is intended primarily for use as a hemostatic agent. Unfortunately, Pawelchak's dispersions do not aerate readily; the freeze-dried foams tend to be brittle and dissolve too quickly.

Japanese patent Application No. 78-145170 describes a method for manufacturing a polyvinyl-alcohol-based sponge material intended for use as an operating sponge for hemostasis. The device is made by foaming aqueous polyvinyl alcohol solution having nonionic cellulose ethers dispersed therein, and freeze drying the foamed mixture at reduced pressure. The foams produced by this method have several disadvantages; they dissolve too rapidly, and upon lyophilization, the product is too stiff. Moreover, the method utilized to manufacture the devices suffers from the same disadvantages discussed above.

Accordingly, a need exists for a bioerodible muco-adherent delivery device that provides for the sustained and/or controlled release of an active ingredient which can be

absorbed through the mucous membrane. Such a device should be convenient to insert, stay in place in the body cavity into which it is inserted, and be comfortable to wear in order to encourage the patient to self-administer the active ingredient.

Furthermore, there is a need for a method of producing such devices whereby the properties of the devices, including density, dissolution time, and active ingredient delivery rate, can be substantially controlled and readily reproduced.

#### Summary of the Invention

It has been found that a device for insertion into a mucosa-lined body cavity comprising, a water-soluble muco-adherent lyophilized foam and an active ingredient, and having a density of about 0.001 to about 0.1 gm/cc and a dissolution time of at least about 8 hours, can provide for the sustained and/or controlled release of an active ingredient for at least 8 hours. Preferably, the device has a dissolution time of at least about 8 hours to about 24 hours, and therefore, is very slow to dissolve. In addition, upon dissolution, the device forms a viscous gels which maintains good structural integrity.

The muco-adherent delivery device of the present invention alleviates many of the problems recited heretofore. It can be easily inserted and manipulated by the patient. When used as a buccal delivery device, it has a very comfortable mouth feel so that the patient does not experience discomfort when using the device. It adheres readily to moist mucosal tissues; thus, it is easy to keep in place. Moreover, the device can provide for the sustained and/or controlled release of active ingredient



into the body cavity for at least several hours. Accordingly, the device provides an ideal means for self-administration of an active ingredient.

5 In addition, the disadvantages associated with prior art methods of manufacture for active-ingredient-dispensing foams are overcome in the present invention. It has been determined that by using a continuous enclosed mixer (known as an Oakes foamer) to foam the dispersion, it is possible to regulate foaming parameters and thereby control the liquid density of the foamed dispersions prior to lyophilization. The inventors have found that by controlling the liquid density of the foamed dispersion, it is possible to achieve excellent control of the dissolution time, dosages, and other properties of the devices. The use of an enclosed foamer like the Oakes foamer for this purpose is heretofore unknown.

20 Accordingly, it is an object of this invention to provide a soluble device for delivery of an active ingredient which delivers an effective dosage of active ingredient across the mucous membrane for at least about 8 hours, and which has a dissolution time of at least about 8 hours.

25 It is another object of this invention to provide a soluble device for delivery of an active ingredient which can be easily inserted by the user, which is muco-adherent, which stays in position for a prolonged period, and which is completely and naturally soluble in the body cavity into which it is inserted, thereby obviating the need for removal.

30 It is a further object of this invention to provide a method for manufacturing the muco-adherent devices

described herein, whereby the method provides for the production of devices having substantially equivalent densities, dissolution times, dosages, and softness and flexibility properties.

5

Further objects and advantages of the present invention will be made known in the following description of the preferred embodiments and claims.

10 Detailed Description of the Invention

The device of this invention comprises a water-soluble muco-adherent lyophilized foam and an active ingredient, wherein the device has a density of about 0.001 to about 0.1 gm/cc and a dissolution time of at least about 8  
15 hours. The devices provide for the sustained and/or controlled release of an active ingredient into a mucosa-lined body cavity for a prolonged period. The term "sustained release" means that the concentration of the active ingredient is maintained at a relatively constant  
20 level in the body cavity. The term "controlled release" means that the active ingredient is administered over a period of time.

As used herein, the term "muco-adherent device" means any  
25 solid substance, of any shape, which is intended to be inserted into a mucosa-lined body cavity and which will adhere to the mucosal tissue thereof. The term "buccal device" or "buccal delivery device" means a muco-adherent device which is intended to be inserted into the buccal  
30 cavity. The term "vaginal device" or vaginal delivery device" means a muco-adherent device which is intended to be inserted into the vagina.

Devices of the invention are intended to be inserted by

the user and do not require fitting by a physician. They can be easily inserted digitally or with an applicator. Furthermore, they are completely and naturally soluble in the body cavity.

5

In use, the device is inserted into the pouch of the cheek or the vagina, and maintained in intimate contact with the mucosal tissue thereof for at least about 8 hours following in-vivo placement. Upon insertion and contact  
10 with the moist mucous membrane, the device naturally and slowly begins to dissolve by fluid absorption. As it dissolves, it continually releases an amount of active ingredient in active form into the body cavity area, at a rate which is sufficient to maintain a therapeutic or  
15 effective level of active ingredient. Preferably, the active ingredient is continually released for at least about 8 hours after insertion.

The device of the invention has good adhesion to the  
20 mucous membrane (i.e., the lining) of the body cavity. Upon contact with the mucus which is excreted by the mucous membrane, the muco-adherent device hydrates, thus adhering the device to the membrane. This feature permits the device to be worn comfortably and maintains it in  
25 proper position so that delivery of the active ingredient is not interrupted.

The active ingredient may be absorbed through the mucosal tissue, thereby avoiding undesirable hepatic first-pass  
30 metabolism and gastrointestinal incompatibility. However, it will be recognized that the active ingredient can also act locally in the body cavity. For example, as will be seen hereinafter, a vaginal delivery device can be used to administer an antifungal or other ingredient for local

- 9 -

treatment of a vaginal infection such as a yeast infection or bacterial infection.

5 Upon dissolution, the lyophilized foam first forms a gel (i.e., a colloidal solution having the consistency of jelly), and then further dissolves into a liquid. The gel so formed possesses good structural integrity for a prolonged period prior to further dissolution to a liquid. For example, at least 2 hours after the devices of the  
10 invention have been placed in 1% saline solution at 37 °C, a substantial amount of gel (at least about 10% by volume) still remains visible to the naked eye. This feature facilitates adhesion of the device, permits it to be used comfortably and helps to control the rate of delivery of  
15 the active ingredient.

The time required for the devices of the invention to attain substantially complete in-vitro dissolution to a liquid (i.e., no gel is evident), as measured by the  
20 method described below, is referred to as "dissolution time". By applying the teachings of this invention, dissolution times of at least about 8 hours can be obtained, preferably at least about 12 hours, even more preferably at least about 20 hours, and most preferably at  
25 least about 24 hours. Moreover, in-vivo dissolution times are likely to be even greater.

The procedure described in USP XXII, 711 DISSOLUTION, Apparatus 1, from U.S. Pharmacopeia, was followed to  
30 determine the dissolution time. This procedure uses an assembly consisting of a covered glass vessel (a Bell jar), a motor, a drive shaft, a basket, and a constant temperature water bath. The speed regulating device used allows the shaft rotation to be selected and maintained at

a rate of 35 rpm. The basket is affixed to the drive shaft. The vessel is filled with 400 ml of 1% (by weight) saline solution (pH 5-6). The device is placed into a dry basket at the beginning of each test, and the basket is  
5 immersed in the vessel containing the saline solution. The vessel is then immersed in a constant temperature water bath set at 37 °C. The sample is observed, and as dissolution takes place, the time for total gelation is recorded. The test is allowed to continue and the time  
10 for total dissolution of the gel is also recorded.

The dissolution time, and other physical characteristics of the devices like density, flexibility and softness, are due to the selection of the particular water-soluble  
15 polymers and active ingredient, their respective amounts, and the novel manufacturing process described herein.

The first step in producing the lyophilized foam devices of the invention comprises forming an aqueous dispersion comprising at least one, and preferably several, water-soluble polymers, and an active ingredient. The term  
20 "aqueous dispersion" as used herein is meant to include dispersions (including solutions) in which the solvent is water and optionally, water-miscible liquids.

25 Preferably, the polymer and the active ingredient are added to the solvent and dispersed. Alternatively, the polymer is initially added to the solvent and dispersed, followed by addition and dispersion of the active  
30 ingredient. If necessary, heat can be applied to the mixture to facilitate dispersion.

Typically, polymer is added to the dispersion at a concentration of about 0.1% to 20% (by weight of the total

dispersion including active ingredient), preferably about 1% to about 15%, even more preferably about 2% to about 10%. At lower concentrations, there may be insufficient polymer to prepare a sturdy foam, whereas at higher concentrations, the dispersion may be too viscous to foam under normal conditions.

Cellulose, cellulose ethers and derivatives thereof, and polymers of the type disclosed in U.S. patent No. 4,615,697, issued to Robinson, and commercially available under the generic name "polycarbophil" are suitable for use in the present invention.

Other suitable polymers include polycarboxylated vinyl polymers, including polyacrylic acid polymers, polyacrylic acid polymers that are lightly crosslinked with a polyalkenyl polyether (such as those commercially available from B. F. Goodrich, Cincinnati, Ohio, under the trademarks Carbopol® 434, 934P, 940 and 941), polysaccharide gums (such as natural plant exudates including e.g., karaya gum, ghatti gum and the like), and seed gums (including e.g., guar gum, locust bean gum, psyllium seed gum and the like). Cross-linked alginate gum gels of the type described in U.S. patent No. 3,640,741, to Etes are also suitable.

Preferably, the polymer is selected from the group consisting of polyurethanes, gelatins, celluloses and cellulose ethers, including hydroxypropylmethylcellulose, sodium carboxymethylcellulose, methylcellulose, hydroxyethylcellulose, hydroxypropylcellulose, hydroxyethylmethylcellulose, hydroxyethylethylcellulose, hydroxypropylethylcellulose, carbopol, polyvinyl alcohol and derivatives thereof, dextran, chitosan and its

derivatives, starch and its derivatives, polyacrylamides, polyacrylates, agar, collagen, fibronectin, alginic acid, pectin, hyaluronic acid, or mixtures thereof.

5 Foams comprised of cellulose ethers are especially preferred. In particular, it has been found that devices comprising hydroxypropylmethylcellulose (HPMC), sodium carboxymethylcellulose (CMC), or mixtures thereof, possess excellent qualities, including good adhesive properties. Devices comprised of foams made from a HPMC, 10 or mixtures of HPMC and CMC, when placed in the buccal cavity of two male volunteers, remained in intimate contact with the mucosa about two hours after insertion.

15 Certain polymers, such as cellulose ethers generally and hydroxypropylmethylcellulose in particular, may be employed to provide liquid foams having good stability and structural integrity, and dry foams with desirable softness. Other polymers, like gelatin, may be 20 incorporated in the devices of the invention to make them sufficiently rigid, so that the device can be inserted without breaking or fracturing. One skilled in the art can readily determine the polymeric ingredients and their amounts that result in a device having the preferred 25 combination of suitable properties.

It has been found that when a mixture of hydroxypropylmethylcellulose and sodium carboxymethylcellulose is used, the polymers preferably 30 are combined in an initial ratio of about 4:1 to about 1:1 (by weight of the dry solids), in order to produce a sturdy, but soft and flexible dry foam. Ratios of about 3:1 to about 2:1 are even more preferred.

Various active ingredients may be incorporated into the devices, including for example, pharmaceuticals, nutrients and diagnostics, but active ingredients comprising pharmaceuticals are preferred. The active ingredient may  
5 be selected from the group of analgesics, anorexics, antiarthritics, antibacterials, antibiotics, anticonvulsants, anti-depressants, antidiabetics, anti-fungal agents, antihistamines, anti-hypertensives, anti-inflammatory, anti-microbials, anti-neoplastics,  
10 anesthetics, anti-virals, cardiovascular, vasodilators, vasoconstrictors, decongestants, diuretics, hormones, muscle relaxants, tranquilizers, polypeptides, vitamins and the like.

15 Hormones and peptides are especially preferred. In an especially preferred embodiment of the device, the active ingredient comprises histrelin or estradiol.

The active ingredient may be provided in the dispersion at  
20 a concentration of about 0.005% to about 25% (by weight of the total dispersion), with about 0.01% to about 10% being preferred. The active ingredient may be present at from about 0.005% to about 95% by weight of the (dry) device, with about 0.1% to about 80% by weight being preferred.  
25 Drug therapeutic value dictates the required concentration of active ingredient.

The amount of active ingredient incorporated into the device affects its therapeutic efficacy, its tactile and  
30 structural properties, and the ease with which it may be manufactured. For example, devices containing relatively high percentages of active ingredient may result in an increase in the level of active ingredient available for absorption through the mucosal tissue. However, if the



active ingredient is too high, such devices may have an inadequate dissolution time and an unpleasant feel. Devices having lower percentages of liquid active ingredient may be too brittle; however, they may possess more desirable dissolution times. If the active ingredient is a solid, such devices may be too brittle to be conveniently inserted. Accordingly, it is necessary to empirically determine the amount of active ingredient that results in a device having the preferred combination of suitable properties.

The devices of the invention may contain additional materials including, but not limited to, preservatives, fillers, excipients, binders, plasticizers, surfactants, wetting agents or penetration agents.

All materials incorporated into the devices should be blended into a homogeneous mixture (in the aqueous dispersion) prior to foaming.

In order to ensure that the aqueous dispersion will subsequently foam, the viscosity of the dispersion should be maintained at about 3000 to 7000 cps, preferably about 3500 to 6000 cps, most preferably about 4000 to 5000 cps, as measured by a Brookfield viscometer at ambient temperature using a number 4 spindle at 20 rpm. Accordingly, it may be necessary to cool the dispersion, preferably to about 32 to 35 °C, with mixing in order to maintain its viscosity.

After all materials to be incorporated into the device have been blended into an aqueous dispersion having adequate viscosity for foaming, the dispersion is transferred to a continuous, enclosed mixer known as an

"Oakes" foamer. An Oakes foamer is capable of operating under pressure to foam the dispersion, and typically is used to manufacture creamy, smooth food products like ice cream and marshmallows. U.S. Patent Nos. 2,572,049, 2,600,569, 2,679,866, and 3,081,069 describe various Oakes foamers useful for practicing the method of the invention, and the disclosures of these patents are incorporated herein by reference. The model referred to as the Oakes 2" Mixer, Model No. # 2MT.5A is especially preferred for use in practicing the invention.

An Oakes foamer is comprised of an electrical system, an air system and a product section. Generally, it comprises a pump; a mixing chamber; a head assembly having a rotor; a gas inlet; an outlet for the foamed dispersion; means to measure pump speed and rotor speed, flow rate, and pressure of an incoming gas; and means to measure the back pressure of the foamed dispersion.

The electrical system consists of a main power switch, and two independently variable speed controllers and motors with digital tachometers to measure the rotor and pump speed.

The air system consists of a manual on/off toggle valve, pressure regulator and gauge, an adjustable flow valve and meter and a one way (check) valve.

The product section consists of a positive displacement pump; speed reducer; inlet piping; a back pressure gauge to monitor back pressure; and a mixing chamber. The back pressure gauge is isolated from the product by a diaphragm seal assembly.

A liquid dispersion is fed to the pump, transmitted through a line to the mixing chamber wherein it is combined with air under pressure, and mixed by the head assembly with the rotor. In the mixing chamber, the dispersion is foamed and the air and the dispersion are blended into a substantially uniform, homogeneous mixture. From the mixing chamber, the foamed dispersion is then sent to an outlet pipe.

It has been determined that the operating parameters of the mixer are primarily responsible for determining the density of the liquid foam, and consequently, the properties of the devices produced. For example, increasing the pressure and/or flow rate of air into a fixed volume of dispersion generally produces a more flexible, faster dissolving device. Similarly, changing the pump speed and/or the rotor speed, also changes the liquid density of the foamed liquid dispersion. The use of an enclosed foamer (like an Oakes foamer) permits each of these process variables to be separately monitored and independently altered in a controlled manner. Thus, it is possible to empirically determine the settings of the foamer which will produce a foamed dispersion having a desirable liquid density and, upon subsequent lyophilization, bioerodible, muco-adherent devices having suitable qualities. Moreover, the use of such a foamer makes it possible to accurately reproduce the settings so that a batch of devices having substantially identical properties and dosages is manufactured in each manufacturing sequence.

It has also been found that the devices of the invention (when they are made by lyophilizing an aqueous solution or dispersion of a water soluble polymer and an active

2105887

- 17 -

material wherein the aqueous solution or dispersion has been foamed prior to lyophilization) should have a (dry) density of about 0.001 to about 0.15 gm/cc, preferably about 0.001 to about 0.08 gm/cc, more preferably about 0.01 to about 0.08 gm/cc, as determined using techniques which are well-known to those of ordinary skill in the art. A device having a density within these ranges possesses a good dissolution time. In addition, such devices are sufficiently sturdy, yet soft and flexible, so that the devices are comfortable to the user and yet do not readily break upon insertion.

When devices of the invention are made by lyophilizing a substantially gas-free, i.e. unfoamed, solution or dispersion of a water soluble polymer and an active material, the dry density of the device should range from about 0.06 g/cc to about 0.30 g/cc, preferably, from about 0.10 g/cc to about 0.16 g/cc.

Typically, in order to achieve devices with good physical characteristics, good dissolution times, and which are sufficiently efficacious at prolonged periods, foamer conditions are set as follows; pump speed about 25-30 rpm, air flow rate about 100-220 cc/min (at 100 psig input pressure), and rotor speed about 1000 - 2300 rpm. The foam that results generates a back pressure of 10-40 psig during extrusion. Of course, the conditions are approximate since operational variability occurs in the meters during operation of the foamer. In addition, the dispersion probably has some air in it due to the dispersion formulation step. Prior degassing will likely alter the density of the solution and require a change in the liquid/air ratio in the foamer.

CHIC-802

Any of these process variables can be changed, thereby changing the liquid density of the foam. In order to determine how the liquid density of the foam as well as the device produced from that foam are affected, foams are  
5 manufactured using the Oakes foamer wherein one process variable is varied while all other parameters remain constant.

For example, a series of foams of varying liquid density  
10 can be produced by varying the flow rate of the incoming gas. The liquid density of the resulting foam is determined using techniques that are well-known in the art. A curve is subsequently generated by plotting the density of the foamed liquid dispersion versus the flow  
15 rate.

The foamed dispersion from each run is then lyophilized (that is, freeze-dried under vacuum). Upon lyophilization, the device (whose foamed liquid density is  
20 known) is evaluated to determine whether it has certain characteristics, including an adequate dissolution time. In this manner it is possible to determine the liquid density which, upon lyophilization, results in a device having a combination of suitable properties. Thus, the  
25 settings necessary to foam the dispersion to the desired liquid density can be readily determined empirically or from the graph, and more importantly, controlled by the operator of the foamer who can easily reset the gas flow rate or any other process variable on the foamer to the  
30 appropriate setting to achieve reproducible results.

Therefore, by using the method of the invention one can substantially control the liquid density of the foamed dispersions, and ultimately, the properties including

dosage, dosage delivery rates and dissolution times of the devices so produced.

5 Foaming can be continued until the back pressure gauge reaches an equilibrium value. Alternatively, one skilled in the art can readily determine when sufficient foaming has occurred by inspecting the viscosity of the foamed dispersion as it is extruded. Preferably, the density of the liquid foamed dispersion should range from about 0.1 to about 1.0 gm/cc. Liquid foam densities of about 0.4 - 10 0.6 gm/cc are even more preferred.

15 In the next step, the foamed liquid dispersion is placed into a receptacle having a known volume ("unit dosage"). Since the liquid density of the foam and the volume of the receptacle are known, it is a simple calculation to determine the foam weight and the amount of active ingredient incorporated into each unit dosage.

20 Accordingly, one skilled in the art can readily manufacture batches of devices containing known and substantially equivalent dosages of active ingredient.

25 Although the foam can be cast into sheet form, it is preferably extruded through tygon tubing into a pre-formed mold. Various aluminum, plastic and release liner covered molds can be employed. Release-coated aluminum molds are preferred, since the devices easily release from these molds without cohesive failure.

30 It is also preferred to extrude the foam into compartmentalized trays whereby the volume of one compartmental unit equals the volume of the resulting device. This prevents uncontrolled spread or flow of the

foam and thus, the manufacture of devices which have nonuniform dimensions and dosages.

5 The foamed dispersion is then lyophilized in a freeze drier in order to generate an open cell foam device which contains the active ingredient. A Virtis 800L-Freezemobile 12 is preferred. The freeze-drier shelves are chilled to below about -40 °C. The condenser is chilled to below about -50 °C. The filled molds are  
10 placed on the shelves and frozen to shelf temperature. The frozen foam is then exposed to the full vacuum (10 - 90 millitorrs) of the unit. Once this vacuum is achieved, the shelf temperature is gradually increased to about room temperature and sublimation continues, preferably for at  
15 least about 15 hours, or until the sample temperature reaches about 20 - 25 °C.

Thermal gravimetric analysis may be used to determine the water content of the foams. It may also be used to  
20 determine the thermal stability of the devices by determining degradative weight loss.

Typically, residual water is present at about 5% by weight of the final dried product.

25 The active ingredient content of the devices may be determined using ultraviolet, HPLC, or any other known analysis of a solution of the dissolved foam, or analysis of the dried bioerodible device.

30 The invention is further illustrated by the following examples which are not intended to be limiting.

#### EXAMPLES

**EXAMPLE 1 - Preparation Of A Histrelin Containing Buccal Delivery Device****STEP 1. Dispersion Preparation**

Deionized water (330 g) was heated to 190 °F. To this 20 g of hydroxypropylmethylcellulose (Methocel E4M-Dow Chemical, Midland, Michigan) was added with stirring. After 5 minutes, 650 g of deionized water cooled to 20°C was added with stirring. The hydroxypropylmethylcellulose was dissolved after the solution had degassed, 750 g was mixed with 1.8 g of histrelin. The mixture was stirred until the histrelin was dissolved.

**STEP 2. Foaming Procedure**

The solution of step 1 was added to the hopper of an Oakes Foamer (Model 2MT. 5A). The solution was pumped through the system at a speed of about 25 rpm until equilibrium was attained. The initial 100 - 150 ml was purged and discarded. The remainder was recirculated. The rotor of the mixing head assembly was set at 1650 rpm and turned on. The air pressure was set at 100 psig and a flow rate of 220 cc/min. The foam was generated at a back pressure of 40 psig and had a measured liquid density of 0.52 gm/cc. The foam was extruded through 1/4" tygon tubing and collected as a cast sheet in a tray having dimensions of 23 x 33 x 0.5 cm. The top of the tray was scraped to eliminate excess foam and to produce a smooth, even surface.

**STEP 3. Lyophilization Procedure**

The liquid foam sample was then placed on the shelf of a Virtis freeze drier (Unitop 800L with Freezemobile 12). These shelves were pre-chilled to -45 °C. The frozen foam was



lyophilized at full vacuum (20-60 millitorr) to a terminal temperature of 20 °C. The drying time was about 16 hours.

#### In-Vitro Foam Dissolution Studies

5 The U.S.P. procedure described heretofore was followed to determine the dissolution times for the devices produced. The devices (400 mg samples) were placed in baskets and immersed in 400 ml of 1% saline solution, in a water bath  
10 set at 37 °C. The dissolution times were recorded upon visual inspection.

#### In-Vivo Delivery Study Of The Histrelin Containing Buccal Delivery Device

15 The study was designed to measure the ability of the histrelin delivered by the soluble buccal devices of the invention to induce ovulation in the diestrus rat. Devices were prepared by punching 7 mm tablets from the tray containing the lyophilized foam. Each tablet  
20 theoretically contained 297 ug of histrelin. Whole, halved and quartered tablets were then placed in the buccal cavity of diestrus rats anesthetized with ether. After 10 minutes the device was absorbed. The following  
25 day the rats were sacrificed and the oviducts removed and examined for the presence of ova.

As shown in Table I below, the tablets were effective in inducing ovulation in a dose-dependent manner with a ED50 dose of approximately 75 ug/rat or 300 ug/Kg.

30

TABLE I

			# of Rats Ovulating
			/Total # of Rats
5	Buccal Tablet	Histrelin, *ug	Ova/Rat
	Whole	300	13
	Half	150	8
	Quarter	75	6

\*micrograms

**EXAMPLE 2 - Preparation Of An Estradiol Containing Buccal Delivery Device**

**STEP 1. Dispersion Preparation**

A solution containing 2% HPMC was prepared as in Example 1. About 0.2 g of estradiol was added with stirring to about 3000 g of a 2% hydroxypropylmethylcellulose solution at 25°C. The solution was stirred for several minutes until all particles were dispersed.

**STEP 2. Foaming Procedure**

The solution of step 1 was added to the hopper of an Oakes Foamer (Model 2MT. 5A). The solution was pumped through the system at a speed of about 55 rpm until equilibrium was attained. The initial 100 - 150 ml was purged and discarded. The remainder was recirculated. The rotor of the mixing head assembly was set at 2150 rpm and turned on. The air pressure was set at 100 psig and a flow rate of 340 cc/min. The foam was generated until a back pressure equilibrium was attained, at which point it had a measured liquid density of 0.46 gm/cc. The foam was extruded through 3/8" tygon tubing and cast into a tray of the dimensions 46.5 x 25.6 x 0.8 cm. The (average) weight of the liquid foam in the tray was 385 g. The liquid flow rate was 479 g/min.

The anticipated dosage was 10ug/7mm diameter unit.

**STEP 3. Lyophilization Procedure**

The same procedure described in Example 1 was repeated.

5

**In-Vivo Delivery Study of The Estradiol Containing  
Buccal Delivery Device**

10 The devices prepared in Example 2 were evaluated in  
ovariectomized Sprague-Dawley rats. The rats were  
ovariectomized 2 weeks prior to testing. On the test day  
the animals were anesthetized with ether and administered  
with either 10 ug of 17 B-estradiol in sesame oil [0.2 ml  
by subcutaneous (S.C.) or ingestion (I.G.) routes] or a  
15 soluble device containing an equal amount of estradiol  
placed buccally. Animals were kept anesthetized for  
approximately 10 minutes after estradiol administration.  
Trunk blood was collected at various times thereafter.  
Serum 17 B-estradiol levels were then measured in a single  
20 radioimmunoassay and are reported in Table II.

TABLE II

SERUM ESTRADIOL LEVELS AFTER ADMINISTRATION OF 10 ug OF  
17 B-ESTRADIOL BY VARIOUS ROUTES TO OVARECTOMIZED RATS  
Hours After Treatment

	0.5	1.0	2.0	4.0
5	Vehicle 8.3 +/-3.8* (Sesame Oil)			
	S.C. 1845 +/-137	1539 +/-264	1286 +/-150	607 +/-195
	I.G. 24 +/-6	18 +/-3	29 +/-6	27 +/-6.0
10	Buccal 258 +/-38	221 +/-63	80 +/-26	35 +/-6
	*picograms per milliliter			

As indicated by the results set forth above, the  
bioavailability of estradiol administered buccally was  
15 greater than oral administration but less than  
administered by injection. However, the observed 3 to 5  
fold increase in the level of bioavailable drug  
administered by the buccal device versus oral  
administration in the first 1 to 2 hours was  
20 significant.

**Example 3**

Using the manufacturing methods described herein, it is  
possible to produce foams having (in-vitro) dissolution  
25 rates of at least about 7.5 hours to at least about 23  
hours. Table III presents data on the dissolution times  
achieved by foams representative of those used in the  
invention (Examples 4-15) and comparative examples  
(Examples 1-3).

30

TABLE III

Sample	Dissolution Time, hours
1. (6% PVA solution)*	7.5
2. (6% PVA foam)*	4
5 3. (3:1:1 gelatin/pectin/CMC)**	4.75
4. (2% HPMC Solution)	23 minimum
5. (2% HPMC, 100 cc/min air)	23 minimum
6. (2% HPMC, 200 cc/min air)	Between 7.5 and 20.5 h
10 7. (2% HPMC, 300 cc/min air)	Between 7.5 and 20.5 h
8. (67/33 HPMC/CMC HP-12HS)	20 minimum
9. (75/25 HPMC/CMC HP-12HS)	20 minimum
10. (67/33 HPMC/CMC HP-5HS, lower MW)	20 minimum
15 11. (75/25 HPMC/CMC HP-5HS)	20 minimum
12. (67/33 HPMC/HP-SB, lower MW)	7.5
13. (75/25 HPMC/HP-SB, lower MW)	7.5
14. (67/33 HPMC/HP-SH, lower MW)	22
15. (75/25 HPMC/HP-SH, lower MW)	22
20	* The percentage indicates the percentage of polymer added to the liquid dispersion by weight (prior to foaming).
25	** The ratio indicates the initial ratio of polymers added to the aqueous dispersion.

30 In comparative Examples 1 and 2, the control solution and the foam was comprised of polyvinylalcohol (Airvol 540, Air Products, Allentown, Pennsylvania) and was prepared in accordance with the teachings of Japanese Patent Application No. 78-145170. The foam of Example 3 was prepared in accordance with the description set forth in U.S. patent No. 4,292,972, Example 3.

- 27 -

Examples 4 - 15 were comprised of foams containing hydroxypropylmethylcellulose (Methocel E4M, obtained from the Dow Chemical Company, Midland, Michigan).

5 Examples 8 - 15 were further comprised of sodium carboxymethylcellulose of various molecular weights including Cellogen HP-12HS, having a molecular weight of 330,000 to 380,000, Cellogen HP-5HS, having a molecular weight of 290,000 to 315,000, Cellogen HP-SB, having a  
10 molecular weight of 75,000 to 83,000, and Cellogen HP-SH, having a molecular weight of 146,000 to 153,000 (each of which are available from Montello, Tulsa, Oklahoma). The preferred carboxymethylcellulose was Cellogen HP-12HS.

15 As the data above shows, the foams of the prior art dissolved in 4 to 7.7 hours. The Sample 3 foam exhibited poor structural integrity. The foam produced in accordance with the teachings of the Japanese Patent Application was too stiff.

20 On the other hand, the foams of the invention were soft and pliable, exhibited good structural integrity over time, and had good bioadhesion. Moreover, as indicated above, they had dissolution times of about 7.5 hours to  
25 over 23 hours. Accordingly, the foams are superior to those prepared in accordance with the prior art.

As indicated earlier herein, various active ingredients can be incorporated into the devices of the present  
30 invention for subsequent delivery of that active ingredient. For example, an antifungal drug may be incorporated into devices of the present invention and the resulting devices used as a vaginal suppository. In use, the device is inserted into the vagina after which

the antifungal ingredient is released so as to function, for example, as a treatment for vaginal yeast infections.

- 5 The following Examples show the preparation of water soluble, muco-adherent vaginal delivery devices containing miconazole nitrate and terconazole, both of which are anti-fungal drugs.

10 EXAMPLE 16

- A water-soluble, muco-adherent drug delivery device comprising miconazole nitrate (MN) was prepared as follows. An aqueous dispersion of miconazole nitrate and hydroxypropylmethyl cellulose (HPMC) was first prepared. 5174 grams of sterile water were added to a 3-gallon stainless steel container fitted with an electric mixer and heated to 180°F. A dry blend of 406 grams of miconazole nitrate and 420 grams of HPMC was gradually added to the heated water with agitation over the course of five (5) minutes. Stirring was continued for a period of five (5) minutes after completion of the addition of the dry blended materials. The resulting dispersion was cooled to room temperature over a period of thirty (30) minutes with continued stirring. The cooled dispersion had a milky coloration, a density of 1.04 g/cc., and a Brookfield viscosity of about 5350 centipoises (cps) when measured using a No. 4 spindle at 10 rpm and 78°F (25.6°C). The dispersion consisted of 7.0% by weight of HPMC, 6.8% by weight of miconazole nitrate and 86.2% by weight of water. The dispersion was substantially free of any entrained air. The HPMC was obtained from Dow Chemical Company under the designation Methocel\* E50-LV Premium. According to the supplier, Methocel\* E50-LV Premium has the following

## characteristics:

- a methoxyl content of 28-30% (ASTM Test Method D3876);
- a hydroxypropyl content of 7.0-12.0% (ASTM Test Method D3876); and
- a viscosity (2% in water @ 20°C) of 40-60 cps (ASTM Test Method D2363).

10 The above described HPMC/MN aqueous dispersion was charged to the hopper of the Oakes foamer machine mentioned in Example 1. The Oakes foamer was used to pump the dispersion into a released-coated aluminum split mold having 120 bullet-shaped mold cavities each having a maximum diameter of about 1 cm and a depth of about 3 cm. The Oakes machine was operated without the introduction into the aqueous dispersion of any compressed gas, i.e., the dispersion delivered to the split mold was not aerated or foamed.

20 The dispersion filled split mold was then placed on a shelf of the VIRTIS freeze drier mentioned in Example 1. The chamber of the freeze drier had been pre-chilled to -44°C. (condenser temperature was -64° C.) The foam was allowed to freeze over a period of about two (2) hours.

25 The frozen foam was then lyophilized (i.e. freeze-dried) at full vacuum (20-60 millitor) to a terminal temperature of 20°C. The lyophilization time was about fifteen (15) hours. The freeze-dried, cylindrical shaped, foam devices were released from the mold cavities and stored in air-tight containers to await further testing. The resulting foam devices, suitable for use as vaginal suppositories, had an average weight of 0.288 grams, were chalky white in color, had a

30



maximum diameter of 0.9 cm, a length of about 2.8 cm and a density of about 0.144 gm/cc.

- 5 Six (6) of the foam devices were tested for In-Vitro  
Foam Dissolution Times in the manner described in  
Example 1 except that the shaft rotation was set at 30  
RPM and the baskets containing the test samples were  
10 immersed in 900 mls. of a citric acid/disodium hydrogen  
phosphate heptahydrate buffer with an ionic strength of  
0.1 M KCl and pH of 4.0. A pH of 4.0 was chosen because  
it is the pH at which miconazole nitrate most readily  
dissolves and because it is in the middle of the pH  
range, i.e. 3 to 5, of the normal healthy vagina.
- 15 The Dissolution Time, average of six determinations, was  
about six (6) hours. Control samples, i.e. the same  
device without miconazole nitrate, had an average weight  
of about 150 mgs., an average Dissolution Time of about  
20 6 hrs and a density of about 0.075 gm/cc. The aqueous  
dispersion foam from which the controls were prepared  
consisted of 7.5% HPMC and 92.5% water.

#### EXAMPLE 17

- 25 A water-soluble, muco-adherent drug delivery device  
comprising terconazole, another anti-fungal ingredient,  
was prepared as follows. An aqueous dispersion of  
terconazole and hydroxypropylmethylcellulose was first  
30 prepared. 2634 gram of sterile water and 30 grams of  
benzyl alcohol were added to a 4 liter glass beaker were  
fitted with an electric mixer and heated to 180°F. A dry  
blend of 120 gm of terconazole (TER) and 216 gms of HPMC  
was gradually added to the heated water with agitation

over the course of five (5) minutes. Stirring was continued for a period of thirty (30) minutes after completion of the addition of the dry blended materials. The resulting dispersion was cooled to room temperature over a period of forty (40) minutes while stirring was continued. The cooled dispersion had a murky coloration, a density of 1.04 gm/cc, and Brookfield viscosity of about 5100 centipoises (cps) when measured using a No. 4 spindle at 10rpm and 78°F. The dispersion consisted of 7.2% by weight of HPMC, 4.0% by weight of terconazole, 1.0% by weight benzyl alcohol and 87.8% by weight of water. The dispersion was substantially free of any entrained air. The HPMC used in this Example 17 was obtained from Dow Chemical Company under the designation Methocel\* E50-LV Premium. The above-described aqueous dispersion containing HPMC, terconazole and benzyl alcohol was charged to the hopper of the Oakes foamer machine mentioned in Example 1. The Oakes foamer was used to pump the dispersion into the same release coated aluminum split mold mentioned in Example 16. As was the case in Example 16, the Oakes machine was operated without the introduction into the aqueous dispersion of any compressed gas, i.e., the dispersion delivered to the split mold was not aerated or foamed.

The dispersion filled split mold was then placed into the freeze drier and subsequently freeze dried and lyophilized in the same manner as set forth in Example 16. Whereas the lyophilization time in Example 16 was about 15 hours, the lyophilization time in this Example 17 was about 17 and 1/2 hours.

The resulting foam devices, also suitable for use as

vaginal suppositories, had an average weight of 0.244 grams, were chalky white in color, had a maximum diameter of about 0.9 cm, and a length of about 2.8 cm. The density of the devices was about 0.122 gm/cc.

5

Six of the foam devices of this Example 17 were tested for their In Vitro foam Dissolution Times in the manner described in Example 16. The dissolution time of the Example 17 devices, average of 6 determinations, was about six (6) hours. Control samples, identical in composition to those referred to in Example 16, also had an average dissolution time of about 6 hours. The invention having now been fully described, it should be understood that it may be embodied in other specific forms or variations without departing from its spirit or essential characteristics. Accordingly, the embodiments described above are to be considered in all respects as illustrative and not restrictive, the scope of the invention being indicated by the appended claims rather than by the foregoing description, and all changes which come within the meaning and range of equivalency of the claims are intended to be embraced therein.

10

15

20

- 33 -

The embodiments of the invention in which an exclusive property or privilege is claimed are defined as follows:

1. A method for administering an active ingredient to the buccal cavity comprising:

- 5 (a) providing a water-soluble, muco-adherent device comprising a solid, soluble lyophilized foam and an active ingredient, said device having a density of about 0.001 to about 0.15 gm/cc and a dissolution time of at least about 8 hours;
- 10 (b) inserting said device into the buccal cavity to adhere to the mucous membrane of the buccal cavity to maintain said device for a prolonged period prior to its natural dissolution;
- 15 whereby the device dissolves so that said active ingredient is released and absorbed through mucosal tissue.

2. The method of claim 1 wherein step (a) comprises providing a device having a dissolution time of at least about 20 hours.

20

3. The method of claim 1 wherein step (a) comprises providing a device comprising a substantially homogeneous mixture of foam and active ingredient.

25

4. The method of claim 1 wherein step (b) comprises providing a device which gels prior to dissolution to a liquid.

30 5. The method of claim 1 further comprising step (c) which comprises permitting said device to completely dissolve in the buccal cavity, whereby the need to remove said device from the buccal cavity is obviated.

- 34 -

6. A soluble device for insertion into the buccal cavity for administering an active ingredient, comprising:

5 a water-soluble muco-adherent lyophilized foam and an active ingredient, said device having a density of about 0.001 to about 0.15 gm/cc and a dissolution time of at least about 8 hours.

10 7. The device of claim 6 wherein said foam is comprised of at least one water-soluble polymer.

15 8. The device of claim 7 wherein said polymer is selected from the group consisting of gelatin, hydroxypropylmethylcellulose, sodium carboxymethylcellulose, methylcellulose, hydroxyethylcellulose, hydroxypropylcellulose, hydroxyethylmethylcellulose, hydroxyethylethylcellulose, hydroxypropylethylcellulose, polyvinyl alcohols, and mixtures thereof.

20 9. The device of claim 6 wherein said foam comprises hydroxypropylmethylcellulose.

25 10. The device of claim 6 wherein said foam comprises hydroxypropylmethylcellulose and sodium carboxymethylcellulose.

30 11. The device of claim 6 wherein said active ingredient comprises a hormone.

12. The device of claim 6 wherein said active ingredient comprises a polypeptide.

13. The device of claim 6 wherein said active ingredient comprises histrelin.

5 14. The device of claim 6 wherein said active ingredient comprises estradiol.

15. The device of claim 6 wherein said active ingredient is present at from about 0.005% to about 95% by weight of the device.

10 16. The device of claim 6 wherein said active ingredient is present at from about 0.1% to about 80% by weight of the device.

15 17. The device of claim 6 having a density of about 0.001 to about 0.08 gm/cc.

18. The device of claim 6 having a density of about 0.01 to about 0.08 gm/cc.

20 19. The device of claim 6 having a dissolution time of at least about 20 hours.

25 20. The device of claim 6 wherein said device comprises a substantially homogeneous mixture of foam and active ingredient.

30 21. An improved method for manufacturing a buccal delivery device for orally administering an active ingredient comprised of water-soluble lyophilized foam and an active ingredient, said method comprising the steps of:

(a) forming an aqueous dispersion comprising at least one water-soluble polymer and at least

- one active ingredient;
- (b) providing a continuous, enclosed mixer capable of operating under pressure to foam the dispersion, said continuous mixer comprising a pump, a mixing chamber, a mixer assembly having a rotor, a gas inlet, an outlet for foamed dispersion, means to measure a rotor speed, a pump speed, a flow rate and pressure of an incoming gas, and mean to measure a back pressure of the foamed dispersion;
- (c) selecting a target density for the foamed liquid dispersion, and a target dosage of active ingredient for the device;
- (d) setting a pump speed;
- (e) setting a rotor speed;
- (f) setting a pressure and flow rate for an incoming gas;
- (g) increasing the viscosity of said dispersion of step (a) until it has a viscosity sufficient to foam;
- (h) transferring said dispersion to said mixer, and then foaming said dispersion until the density of the dispersion is substantially equal to the target density;
- (i) measuring the back pressure of the foamed dispersion;
- (j) placing said foamed dispersion into a receptacle of known volume; and
- (k) lyophilizing said dispersion to produce a lyophilized foam;

whereby the dosage of active ingredient in the lyophilized foam is substantially equal to the target dosage.

22. The method of claim 21 wherein the liquid density of the foamed dispersion of step (h) is from about 0.1 to about 1.0 gm/cc.

5 23. The method of claim 21 wherein the liquid density of the foamed dispersion of step (h) is about 0.5 gm/cc.

24. The method of claim 21 wherein step (a) comprises providing a dispersion comprising  
10 hydroxypropylmethylcellulose and sodium carboxymethylcellulose in a ratio of about 4:1 to about 1:1 by weight.

25. The method of claim 21 wherein step (a) comprises providing polymer in the dispersion at about 0.1% to about 20% by weight.  
15

26. The method of claim 21 wherein step (a) comprises providing polymer in the dispersion at about 1% to about 15% by weight.  
20

27. The method of claim 21 wherein step (a) comprises providing polymer in the dispersion at about 2% to about 10% by weight.  
25

28. The method of claim 21 wherein step (j) comprises extruding said dispersion into a compartmentalized tray comprised of identical units of known volume, whereby the dosage of active ingredient in each unit is  
30 substantially equal to the target dosage.

29. The method of claim 21 wherein the foamed dispersion is lyophilized in a freeze-drier at full vacuum for at least 15 hours.



30. The product produced by the method of claim 21.

31. A method for administering an active ingredient to the vagina comprising:

- 5       (a) providing a water-soluble, muco-adhesive device comprising a solid, soluble lyophilized foam and an active ingredient, said device having a density of about 0.06 to about 0.30 gm/cc and a dissolution time of at least about 8 hours;
- 10       (b) inserting said device into the vagina to adhere to the mucous membrane of the vagina to maintain said device for a prolonged period prior to its natural dissolution;

15       whereby the device dissolves so that said active ingredient is released and absorbed through mucosal tissue.

32. The method of claim 31 wherein step (a) comprises providing a device comprising a substantially  
20       homogeneous, substantially gas-free mixture of a water-soluble polymer and an active ingredient.

33. The method of claim 31 wherein step (b) comprises providing a device which gels prior to dissolution to a  
25       liquid.

34. The method of claim 31 further comprising step (c) which comprises permitting said device to completely  
30       dissolve in the vagina, whereby the need to remove said device from the vagina is obviated.

35. A soluble device for insertion into the vagina for administering an active ingredient, comprising:  
      a water-soluble, muco-adherent lyophilized foam and

an active ingredient, said device having a density of about 0.06 to about 0.30 gm/cc and a dissolution time of at least about 8 hours.

- 5 36. The device of claim 35 wherein said foam is comprised of at least one water-soluble polymer.
- 10 37. The device of claim 36 wherein said polymer is selected from the group consisting of gelatin, hydroxypropylmethylcellulose, sodium carboxymethylcellulose, methylcellulose, hydroxyethylcellulose, hydroxypropylcellulose, hydroxyethylmethylcellulose, hydroxyethylethylcellulose, hydroxypropylethylcellulose, polyvinyl alcohols, and
- 15 mixtures thereof.
38. The device of claim 35 wherein said foam comprises hydroxypropylmethylcellulose.
- 20 39. The device of claim 35 wherein said active ingredient comprises miconazole nitrate.
40. The device of claim 35 wherein said active ingredient comprises terconazole.
- 25 41. The device of claim 35 having a density of about 0.07 to about 0.20 gm/cc.
42. The device of claim 35 having a density of about
- 30 0.10 to about 0.16 gm/cc.